


This listing of claims will replace all prior versions, and listings of claims in the application:

**Listing of Claims:**

Claims 1-6. (Cancelled)

Claim 7. (Currently Amended) A polyurethane composition which cross-links via silane polycondensation and comprises

- A) at least one alkoxy silane-functional polyurethane having end groups corresponding to formula (I)




wherein

R<sup>1</sup> represents an organic group having 1 to 12 carbon atoms,

n is an integer from 2 to 4 and

X, Y, Z represent identical or different organic groups, provided that at least one of the groups is an alkoxy group having 1 to 4 carbon atoms,

- B) at least one filler,  
C) at least one reaction product of  
i) at least one aminosilane corresponding to formula (II)



wherein

R<sup>2</sup> represents a hydrogen atom or an aminoethyl group

n is 3 and

Mo6862

- 2 -

X, Y, Z have the meanings set forth for formula (I),

with

ii) at least one maleic or fumaric ester corresponding to formula (III)




wherein

[[R<sub>3</sub>]] R<sup>3</sup> represents an alkyl group having 1 to 12 carbon atoms, and



D) at least one organometallic compound.

Claim 8. (Currently Amended) The polyurethane composition of Claim 7 wherein [[R<sub>1</sub>]] R<sup>1</sup> represents a group corresponding to formula (IIb)



wherein [[R<sub>4</sub>]] R<sup>4</sup> denotes an alkyl group having 1 to 4 carbon atoms.

Claim 9. (Currently Amended) The polyurethane composition of Claim 7 wherein component C) comprises an aminosilane compound corresponding to formula (V)



wherein

[[R<sub>3</sub>]] R<sup>3</sup> represents a linear or branched aliphatic hydrocarbon group having at most 12 carbon atoms,

n is 3 and

X, Y and Z represent methoxy or ethoxy groups.

Claim 10. (Previously Presented) The polyurethane composition of Claim 7 wherein X, Y and Z each represent a methoxy or ethoxy group.

Claim 11. (Previously Presented) The polyurethane composition of Claim 8 wherein X, Y and Z each represent a methoxy or ethoxy group.

Claim 12. (Previously Presented) The polyurethane composition of Claim 9 wherein X, Y and Z each represent a methoxy or ethoxy group.

Claim 13. (Previously Presented) The polyurethane composition of Claim 7 wherein X, Y and Z each represent a methoxy group in component A).


Claim 14. (Previously Presented) The polyurethane composition of Claim 8 wherein X, Y and Z each represent a methoxy group in component A).

Claim 15. (Previously Presented) The polyurethane composition of Claim 9 wherein X, Y and Z each represent a methoxy group in component A).

Claim 16. (Currently Amended) A process for the preparation of the polyurethane composition of Claim [[1]] Z which comprises mixing components A), B), and [[E]] D) with exclusion of moisture and subsequently adding component C, the reaction product of i) and ii).


Claim 17. (Currently Amended) A polyurethane composition which cross-links via silane polycondensation and comprises


- A) at least one alkoxy silane-functional polyurethane having end groups corresponding to formula (I)



wherein

R<sup>1</sup> represents a group corresponding to formula (IIb)





(IIb),

wherein  $[[R_4]]$   $R^4$  represents an ethyl group.


$n$  is 3 and

$X, Y, Z$  represent methoxy or ethoxy groups,

B) at least one filler,

C) at least one reaction product of

i) at least one aminosilane corresponding to formula (II)



wherein

$R^2$  represents an aminoethyl group and

$n, X, Y, Z$  have the meanings set forth for formula (I),

with

ii) at least one maleic or fumaric ester corresponding to formula (III)



wherein

$[[R_3]]$   $R^3$  represents an alkyl group having 1 to 12 carbon atoms,

and

D) at least one organometallic compound.